

Fermi Surfaces, Fermi Patches, and Fermi Arcs in High T_c Superconductors

M. R. Norman

Materials Science Division, Argonne National Laboratory, Argonne, IL 60439

Abstract. A defining property of metals is the existence of a Fermi surface: for two dimensions, a continuous contour in momentum space which separates occupied from unoccupied states. In this paper, I discuss angle resolved photoemission data on the cuprate superconductor BSCCO and argue that it is not best thought of in this conventional picture. Rather, the data are consistent with “patches” of finite area connected by more conventional “arcs”. Novel physics is associated with the patches, in that the states contained in a patch are dispersionless and thus interaction dominated. In the pseudogap phase, the patches are gapped out, leaving the Fermi arcs disconnected. This unusual situation may be the key to understanding the microscopic physics of the high temperature superconductors, in that the pairing correlations are strongest in the patches, yet the superfluid density lives only on the arcs.

Perhaps no problem in recent history has captured the attention of the condensed matter physics community as much as that of the high temperature cuprate superconductors. After over a decade of work, it has become clear that conventional metal physics alone is not capable in describing all of their properties. In fact, it is strongly felt in a section of the community that new physics needs to be developed to fully solve the problem [1]. One difficulty has been to properly define what the problem to be solved exactly is. For instance, it is now generally accepted by the community that conventional metal physics should not break down for a two dimensional metal which exhibits a free electron dispersion [2]. This can be contrasted with the unusual excitations associated with the fractional quantum hall effect, including that of the still debated half integral case, which arise due to the degeneracy of states in an applied magnetic field (Landau levels). This points to the reasonable hypothesis that the novel physics associated with the high temperature cuprate superconductors has something to do with a dramatic departure of their dispersion from that of free electron metals.

The experimental tool to employ in this regard is angle resolved photoemission spectroscopy (ARPES). For two dimensional materials, if the impulse approximation is valid, then the ARPES intensity should be proportional to the product of the single particle spectral function and the Fermi function [3]. The 2D condition is almost certainly satisfied in the cuprates, in that there is no evidence, particularly

in BSCCO, for any c-axis dispersion in the data. For the photon energies typically employed, there is also evidence that the impulse approximation is satisfied. This is a result of the large number of available final states (due to the complexity of the crystal structure) coupled with the short escape depth of the photoelectrons (which limits the time for the photoelectron to interact with the photohole). As a consequence, the probe is surface sensitive, which has limited much of the most useful data to BSCCO, given its strongly two dimensional nature, with resulting cleaved surfaces characteristic of the bulk.

The importance of the single particle spectral function is self evident. It is the most fundamental quantity predicted by a many-body theory. Being proportional to the imaginary part of the Greens function, it can in principle be Kramers-Kronig transformed to yield the entire Greens function, which in turn defines the electron self-energy, the function that encapsulates the many-body physics of the material. The self-energy implicitly contains the energy dispersion, which as argued above, has strong relevance to the nature of the ground and excited states of the system.

Although ARPES only reveals the occupied part of the spectral function, we are fortunate in the cuprates in that scanning tunneling microscope (STM) measurements in BSCCO yield spectra which strongly resemble that from ARPES for the appropriate bias sign despite the fact that STM is a momentum averaged probe. This indicates that the tunneling matrix elements weight the spectra to certain regions of the Brillouin zone (to be identified later as the patches). Thus, not only do these data provide a useful complement to ARPES data, with the additional advantage of spatial resolution and much higher energy resolution, they can be additionally exploited to obtain crucial information concerning the unoccupied part of the spectral function.

With this introduction, we now turn to some general observations concerning ARPES data in Bi2212. The identification of what the actual Fermi surface is in this material is still of some controversy. This is easy to understand from early measurements of the Stanford group [4]. In a very illuminating figure of a paper by that group (Fig. 2), they show those regions of the Brillouin zone where spectral weight is seen within 50 meV of the Fermi energy, which was comparable to their energy resolution. They then interpreted this in terms of two conventional Fermi surfaces, an electron-like surface centered at the $(0,0)$ point of the zone, and a hole-like surface centered at the (π,π) point of the zone. This was conjectured to be due to the predicted bilayer splitting of the electronic structure due to the two CuO planes per bilayer unit. Subsequent measurements by the UIC-Argonne group [5] were able to attribute the Fermi crossing of the presumed electron-like sheet along $(0,0) - (\pi,0)$ to actually be that of a ghost image of the Fermi surface due to diffraction of the outgoing photoelectrons by the superstructure associated with the BiO surface layer. This led to what is now the mostly accepted picture of just a single hole-like surface centered around (π,π) , with the surprising result that somehow, the c-axis kinetic energy associated with bilayer splitting is missing in the dispersion of the spectral function.

I will now argue that this more or less conventional picture has been accepted

a bit too readily. As stated above, what the authors of Ref. [4] actually show is a plot of the near Fermi energy spectral weight in the zone. This plot is highly instructive. What is seen is a mass of states in the vicinity of the $(\pi, 0)$ points of the zone connected by more typical Fermi surface segments. That is, the most natural interpretation of the data is not that one has a Fermi surface that represents a continuous contour in momentum space. Rather, it appears that one has “Fermi patches” which occupy a finite *area* in momentum space, connected by “Fermi arcs” which resemble more typical behavior. This observation is reinforced by directly looking at the raw spectra. There, one sees that states in the “patch” region in the normal state are characterized by very broad linewidths which exhibit little dispersion. In fact, the often quoted “Fermi crossing” along the $(\pi, 0) - (\pi, \pi)$ direction is based not on dispersion, but rather on the drop in intensity of the spectra along this direction as would be expected from such a crossing.

This behavior becomes even more unusual in the superconducting state. Along the traditionally accepted hole-like Fermi contour, one sees a dispersion consistent with a superconducting order parameter of the $d_{x^2-y^2}$ form [6,7]. But in the “patch” region, one finds a narrow quasiparticle peak with little if any observable dispersion at an energy location given by the maximum of the d-wave gap [8]. This is separated by a spectral dip from a higher binding energy feature, the “hump”, which does in fact have strong dispersion in the “patch”. This dispersion becomes quite obvious in underdoped materials [9] where it begins to take on qualities reminiscent of the undoped magnetic insulator [10].

It is of interest to note that the quasiparticle peak only forms below T_c ; that is, the Fermi liquid superconducting state appears to arise from a non Fermi liquid normal state. This is most dramatic in the underdoped case, where a spectral gap already exists in the normal state in the patches [11–13]. In this case, one finds a strongly incoherent spectrum above T_c , which loses any resemblance to even a very broad peak as the doping is reduced. Yet, despite this, one finds the rather surprising presence of a sharp leading edge gap. This is a non-trivial finding which has yet to be reproduced by any theory which purports to explain the pseudogap. Below T_c , a quasiparticle peak forms at this gap edge. This is somewhat reminiscent of the formation of a bound state inside of a gap, which has suggested a composite nature for the incoherent weight beyond the gap edge [14]. Above T_c , the spectral gap “fills in”, leading to a more or less flat spectrum at a characteristic temperature T^* [15]. This filling in effect is also inferred from specific heat data [16], and directly observed as well by STM [17] and c-axis optical conductivity [18].

The filling in seen in the patch region can be modeled by a very simple self-energy of the form $\Sigma = -i\Gamma_1 + \Delta^2/(\omega + i\Gamma_0)$ [19]. Γ_1 is a crude (i.e., frequency independent) approximation to the single particle scattering rate, which is extremely large in the normal state, and collapses precipitously in the superconducting state, strongly suggesting that electron-electron interactions determine the spectral lineshape. Γ_0 describes the filling in effect, and is found to be proportional to $T - T_c$, as would be expected if it represented an inverse pair lifetime. Δ , the gap parameter, is found to be essentially temperature independent for underdoped samples, as was

inferred earlier from specific heat data [16] and also observed by STM [17]. T^* is then simply the temperature at which Γ_0 becomes comparable to Δ , and thus does not represent a mean field transition temperature, despite its correlation with Δ [20]. Similar modeling has been found to describe STM [21] and c-axis optical conductivity [22] data. This indicates that these probes are weighted towards the patch regions of the Brillouin zone.

The above behavior can be contrasted with what occurs on the Fermi “arcs”, which are the Fermi contour segments which connect the patches. On the arcs, Δ closes in a more or less BCS like fashion [19], and this occurs somewhat above T_c for underdoped samples. This behavior is found in the patch region only for overdoped samples. It is still an unresolved question experimentally whether Δ collapses at the same temperature along the entire arc, though this is a distinct possibility. It is interesting to note that the temperature at which this collapse occurs is similar to the temperature at which the high frequency superfluid response vanishes for an underdoped sample with a similar T_c [23]. This is consistent with the fact that the low energy states in the patch region are dispersionless; that is, the patches probably do not contribute to the superfluid density. Therefore, once Δ collapses on the arcs, the system no longer exhibits a superfluid response, even at high frequencies. The available ARPES data also point to an increase of the size of the patch region as the doping is reduced, with a consequent decrease in the length of the arcs. Once the patches “grab up” the entire zone, the metal collapses into the Mott insulating phase.

The novelty of these findings cannot be overemphasized. If one looks at the anisotropy of the gap at low temperatures, it traces out a d-wave form. This occurs even for underdoped samples [24]. That is, it appears as if there is only a single gap in the problem. Above T_c , though, there appears as if there are two gaps in underdoped samples, a more or less conventional superconducting gap along the Fermi arcs, and a temperature independent one in the patch regions. Yet, at any given $\mathbf{k}$ point, the gap smoothly evolves with temperature, even through T_c . This behavior is impossible to understand from a mean field viewpoint, and simply cannot be fixed up by attributing the gap in the patch region to some other effect (SDW, CDW, etc.). This is reinforced by the fact that once the gap collapses on the arcs, the resulting Fermi surface is just a set of disconnected segments, and therefore not derivable from a mean field description which would have implied a continuous Fermi contour in momentum space [15].

This brings up the important question of what theoretical implications these findings have. A phenomenological model based on the arc-patch picture has been developed by Geshkenbein, Ioffe, and Larkin [25]. The results differ significantly in the pseudogap phase above T_c from standard models of superconducting fluctuations, since the patch regions, because of their dispersionless nature, do not support classical fluctuations. Their model provides a good framework for addressing various data in the underdoped regime. Another phenomenological approach has been advocated by Lee and Wen [26]. They observe that the superfluid density can be written in the form $\rho_s(T) = \rho_s(0) - \alpha T$, with the second term due to quasiparticle

excitations about the d-wave nodes. As α is proportional to the inverse of Δ , and $\rho_s(0)$ is proportional to x (the number of doped holes), then assuming that Δ is roughly independent of doping, one obtains the result that $T_c \sim x\Delta$ in the under-doped regime. As a consequence, $\mathbf{k}$ points where $\Delta_{\mathbf{k}} > \sim T_c$ have spectral gaps which survive above T_c . That is, one has gapless Fermi arcs with gapped patch regions. It is interesting that this argument, though completely consistent with ARPES data, is made independent of such data.

On a microscopic level, the Lee-Wen picture can be motivated by a gauge theory approach to the t-J model [27]. This picture implies a d-wave gap at low T, but a collapse of the gap along the arc above T_c , very similar to what is seen by ARPES. The disconnected Fermi arcs are a consequence of strong fluctuations given the near degeneracy such a model predicts between the d-wave and flux phase states. The doping dependence of the arcs has been calculated in a related gauge theory approach [28] and is consistent with the ARPES doping trend discussed above. A different approach for describing the arc-patch behavior based on the t-J model has been offered by Furukawa, Rice, and Salmhofer [29]. Their results, utilizing a renormalization group treatment of interactions in the patches, suggest a phase separation in momentum space, with an insulating spin liquid phase in the patch regions connected by Fermi arcs, and is motivated by studies of three leg ladders. Finally, there has been a recent study by Putikka, Luchini, and Singh [30] where the momentum distribution, $n_{\mathbf{k}}$, for the t-J model has been obtained by high temperature expansion. The resulting contour plots show that the sharp drop in $n_{\mathbf{k}}$, which defines Fermi crossings, is only well defined on the arcs, very reminiscent of the ARPES data.

In this connection, the work of Khodel and Shaginyan deserves mention [31]. These authors discovered another solution besides the classic Landau Fermi liquid one. This solution is characterized by a flat band which is pinned to the chemical potential, either along a line, or in an entire region of the zone. This Fermion condensate tends to be realized by interactions which are long range in real space and attractive [32], and as a consequence is unstable to superconductivity at low temperatures. In the resulting superconducting state, dispersionless quasiparticle peaks are found, much like what is seen by ARPES in the region of the zone surrounding $(\pi, 0)$ [8]. Above T_c , one expects very broad spectral lineshapes [32], again consistent with ARPES results. In addition, $n_{\mathbf{k}}$ is predicted to have a ramp-like behavior for states inside of the Fermion condensate (patch). This behavior is descriptive of that observed for the frequency integrated ARPES weight along the $(\pi, 0) - (\pi, \pi)$ direction. Therefore, the Khodel state may indeed be the appropriate non Fermi liquid reference state for the patch regions of the zone.

The author thanks his collaborators, Juan Carlos Campuzano, Hong Ding, and Mohit Randeria, for the many discussions which led to the ideas presented here. Also, the author thanks Victor Khodel and Grisha Volovik for discussions concerning the Khodel state. This work was supported by the U. S. Dept. of Energy, Basic Energy Sciences, under contract W-31-109-ENG-38.

REFERENCES

1. P. W. Anderson, *The Theory of Superconductivity in the High T_c Cuprates* (Princeton Univ. Pr., Princeton, 1997).
2. J. R. Engelbrecht and M. Randeria, Phys. Rev. Lett. **65**, 1032 (1990).
3. M. Randeria *et al.*, Phys. Rev. Lett. **74**, 4951 (1995).
4. D. S. Dessau *et al.*, Phys. Rev. Lett. **71**, 2781 (1993).
5. H. Ding *et al.*, Phys. Rev. Lett. **76**, 1533 (1996).
6. Z.-X. Shen *et al.*, Phys. Rev. Lett. **70**, 1553 (1993).
7. H. Ding *et al.*, Phys. Rev. B **54**, R9678 (1996).
8. M. R. Norman *et al.*, Phys. Rev. Lett. **79**, 3506 (1997).
9. J. C. Campuzano *et al.*, unpublished.
10. F. Ronning *et al.*, Science **282**, 2067 (1998).
11. D.S. Marshall *et al.*, Phys. Rev. Lett. **76**, 4841 (1996).
12. H. Ding *et al.*, Nature **382**, 51 (1996).
13. A. G. Loeser *et al.*, Science **273**, 325 (1996).
14. R. B. Laughlin, Phys. Rev. Lett. **79**, 1726 (1997).
15. M. R. Norman *et al.*, Nature **392**, 157 (1998).
16. J. W. Loram *et al.*, J. Supercond. **7**, 243 (1994).
17. Ch. Renner *et al.*, Phys. Rev. Lett. **80**, 149 (1998).
18. C. C. Homes *et al.*, Physica C **254**, 265 (1995).
19. M. R. Norman, M. Randeria, H. Ding, and J. C. Campuzano, Phys. Rev. B **57**, R11093 (1998).
20. H. Ding *et al.*, J. Phys. Chem. Solids **59**, 1888 (1998).
21. M. Franz and A. J. Millis, Phys. Rev. B **58**, 14572 (1998).
22. C. Bernhard *et al.*, Phys. Rev. B **59**, R6631 (1999).
23. J. Corson *et al.*, Nature **398**, 221 (1999).
24. J. Mesot *et al.*, unpublished.
25. V. B. Geshkenbein, L. B. Ioffe, and A. I. Larkin, Phys. Rev. B **55**, 3173 (1997).
26. P. A. Lee and X.-G. Wen, Phys. Rev. Lett. **78**, 4111 (1997).
27. X.-G. Wen and P. A. Lee, Phys. Rev. Lett. **80**, 2193 (1998).
28. X. Dai and Z.-B. Su, Phys. Rev. Lett. **81**, 2136 (1998).
29. N. Furukawa, T. M. Rice, and M. Salmhofer, Phys. Rev. Lett. **81**, 3195 (1998).
30. W. O. Putikka, M. U. Luchini, and R. R. P. Singh, Phys. Rev. Lett. **81**, 2966 (1998).
31. V. A. Khodel and V. R. Shaginyan, JETP Lett. **51**, 553 (1990).
32. P. Nozieres, J. Phys. I France **2**, 443 (1992).